

ZIBO JINGGAN REFRACTORY IMPORT AND EXPORT CO.,LTD

Address:NO. 3, Yanhe Road, Boshan, Zibo, Shandong, China
Email:wp@cnjingganrefractory.com/sdwenping@163.com
Contact:Rose Tel/Wechat:+86-13275332819
Tel:86-533-4188518 Fax:86-533-4188518

Mullite Refractory Ball



1. Main performance parameters

ITEM	UNIT	TECHNCIAL INDEX
MRB-75		
Al ₂ O ₃	%	≥75
Fe ₂ O ₃	%	≤1.2
Porosity	%	≤20
Density	g/cm ³	≥2.4
Compressive strength	Mpa	≥160
Refractoriness	°C	1790
Reheating linear change rate	%	1450°C*3h,±0.3
Refractoriness under load	°C	≥1550
Thermal shock stability	950°C,air cooling,times	≥40

2. Introduction: Mullite Refractory Ball is made of high-quality mullite, Calcined Bauxite, clay as the main raw material, through mixing and sintering with special forming process. Mullite Refractory Ball has high mechanical strength, high temperature resistance, heat shock resistance, wear resistance, slag corrosion resistance, etc. the application effect is excellent in reducing exhaust gas temperature, realizing heat exchange direction and energy saving

ZIBO JINGGAN REFRACTORY IMPORT AND EXPORT CO.,LTD

3. Application of Mullite Refractory Ball: Iron and steel industry hot blast furnace, chemical fertilizer plant transformation furnace, transformation furnace and non-ferrous metal smelting, cement industry
4. Features of Mullite Refractory Ball:
 - 1) high temperature resistance
 - 2) Good thermal shock resistance
 - 3) Good alkali resistance and slag corrosion resistance
 - 4) Energy saving and environmental protection
5. Specification: $\phi 15 \sim 60 \text{mm}$
6. Good feedback of product use effect, the products have been exported to Mexico, Morocco and India.
7. We are a professional supplier, who can provide customers with free product technology, use and other issues.

Do you want to find a professional supplier of refractory products?

Do you want to find a professional supplier of graphite electrodes?

Do you want to find a stable and credible supplier?

Then let's contact with jinggan company

Contact me: Email: wp@cnjingganrefractory.com / sdwenping@163.com

TEL: 86-0533-4188518 / FAX: 86-0533-4188518

Rose: +86-13275332819 (wechat/whatsapp number)